



## Test Report

**FORCE-Dantest CERT**

Wencon ApS  
Jyllandsvej 15  
DK-5400 Bogense

File No. 133224/m1493-681  
Date 2000-03-01  
Page 1 of 1  
Enclosure 0  
KG/BR



**FORCE**  
INSTITUTE

FORCE Institute hereby informs you about the result of the testing of 5 pieces of steel pipe delivered to us on 16th February 2000.

The pipes had an outside diameter of approx. 50 mm and a length of approx. 260 mm and they were numbered 2, 3, 5, 6 and 8 respectively.

The pipes were closed in both ends with a welded end plate - one solid and one with a threaded hole, and each pipe had a wrapped bandage with a total width of approx. 90 mm. According to statement the bandages were placed to cover bored holes with diameter 5 mm.

To each pipe an increasing internal water pressure was applied up to 240 bar at room temperature.

All the bandages leaked water at a pressure lower than 240 bar but after releasing the pressure of 240 bar no visible defects were observed on the bandages.

The pressures where the bandages showed leakage are stated in the table below.

Pipe No.	Leakage occurred at
2	155 bar
3	160 bar
5	175 bar
6	169 bar
8	158 bar

FORCE Institute  
Inspection and Testing

Kjeld Grønfeldt  
B.Sc. (Mech. Eng.)

Extracts from the Test Report may only be reproduced with a written permission from this Institute.  
The test results relate only to the items tested.

The "General Conditions" on the reverse page are an integral part of our services.

456.E. 02.97

Copenhagen  
Main Office  
Park Allé 345  
DK-2805 Broenoby  
Tel. + 45 43 26 70 00  
Fax + 45 43 26 70 11  
e-mail force@force.dk  
www.force.dk

Esbjerg  
Oestre Gjesingvej 7  
DK-6715 Esbjerg N  
Tel. + 45 76 10 06 50  
Fax + 45 75 45 00 86

Vejle  
Navervej 1  
DK-6600 Vejle  
Tel. + 45 76 96 16 00  
Fax + 45 75 36 41 55

Aalborg  
Niels Jernes Vej 2-4  
DK-9220 Aalborg Oe  
Tel. + 45 96 35 08 00  
Fax + 45 96 35 08 29

Aarhus  
Kongsvang Allé 43  
DK-8000 Aarhus C  
Tel. + 45 87 34 02 00  
Fax + 45 87 34 02 19

Helsingborg  
Branch  
Karibgatan 30  
S-254 67 Helsingborg  
Tel. + 46 42 15 21 40  
Fax + 46 42 16 13 20

STK Inter Test AB  
Subsidiary  
Tallmätargatan 7  
S-721 34 Västerås  
Tel. + 46 21 18 02 70  
Fax + 46 21 18 02 02

Affiliated with the Danish Academy of Technical Sciences